

VOC Testing Laboratory

Sample ID: Quiet Glue #1F
Date: 04/16/2013
Client: Sunder Ram
Serious Energy Inc.
Sunnyvale, CA 94089
408-220-5277
sram@seriousenergy.com

SCAQMD 304 Test Summary

Density by ASTM D1475	1038.2 g/L
<i>Pycnometer Method</i>	
Volatile Portion by ASTM D2369	23.7 % mass
<i>Mass loss at 110°C for 60 minutes</i>	
Water by ASTM D3792	31.4%
Exempted Compounds by SCAQMD 303	0 g/L (none found)
<i>Acetone, p-chlorobenzotrifluoride, methyl acetate, and t-butyl acetate</i>	
<i>GC/MS Chromatogram Attached</i>	

Final Test Result	<0.1 g/L VOC
-------------------	--------------

Leonard E. Orzech
Senior Chemist